

**Amendments to the Claims:**

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1-13. (Canceled)

14. (Currently Amended) A composite material member comprising:

a main material composed of a light metal or a light metal alloy which can be molded by casting; and

a secondary material composed of a metallic material different from the main material ~~or an inorganic material~~, the secondary material being joined to the main material by integrally casting with the main material,

wherein a porous material is arranged on a part of a boundary area or an entire boundary area between the main material and the secondary material,

wherein the light metal is aluminum or magnesium, and the light metal alloy is an alloy including at least one of aluminum and magnesium,

wherein the secondary material is cast iron, iron steel, stainless steel, Fe-Cr-based alloy, or Ni-based alloy,

~~and wherein~~ wherein the porous material is composed of a metal fiber and a foamed metal by which a diffusion joining can be performed with the secondary ~~material.~~ material, and

wherein the porous material has a uniform volume rate, the volume rate is from 30 to 60% when a plate thickness of a portion of the porous material which contacts the secondary material in a direction spaced from the secondary material is not less than 1 mm and less than 2 mm, and

the volume rate is from 20 to 60% when a plate thickness of a portion of the porous material which contacts the secondary material in a direction spaced from the secondary material is not less than 2 mm.

15. (Previously Presented) The composite material member according to claim 14, wherein the metal fiber is laminated randomly or in an oriented condition to yield a three-dimensional structure.

16. (Currently Amended) The composite material member according to claim 14, wherein the metal fiber has a wire diameter of from a few micrometers to 100 micrometers, and the metal fiber ~~and the whisker have~~ has a grain size of from a few micrometers to 100 micrometers.

17-19. (Canceled)

20. (Currently Amended) A method for producing a composite material member comprising the steps of :

preparing a main material composed of a light metal or a light metal alloy which can be molded by casting, and a secondary material composed of a metallic material different from the main material ~~or an inorganic material~~; and

joining the secondary material to the main material by integrally casting the materials;

wherein a porous material is contacted with the secondary material, the porous material and the secondary material are compressed at a predetermined volume rate and sintered in the contacted condition to join them by diffusion and obtaining a compact, and the compact is joined to the main material by integrally casting ~~them~~ them; and

wherein the porous material has a uniform volume rate, the volume rate is from 30 to 60% when a plate thickness of a portion of the porous material which contacts the

secondary material in a direction spaced from the secondary material is not less than 1 mm and less than 2 mm; and

the volume rate is from 20 to 60% when a plate thickness of a portion of the porous material which contacts the secondary material in a direction spaced from the secondary material is not less than 2 mm.

21. (Currently Amended) A method for producing a composite material member comprising the steps of :

preparing a main material composed of a light metal or a light metal alloy which can be molded by casting, and a secondary material composed of a metallic material different from the main material ~~or an inorganic material~~; and

joining the secondary material to the main material by integrally casting the materials;

wherein a porous material composed of a fiber is preliminarily compressed at a predetermined volume rate, the compressed fiber and the secondary material are sintered, thereby joining them by diffusion and obtaining a compact, and the compact is joined to the main material by integrally casting ~~them~~ them, and

wherein the porous material has a uniform volume rate, the volume rate is from 30 to 60% when a plate thickness of a portion of the porous material which contacts a secondary material in a direction spaced from the secondary material is not less than 1 mm and less than 2 mm;

and the volume rate is from 20 to 60% when a plate thickness of a portion of the porous material which contacts the secondary material in a direction spaced from the secondary material is not less than 2 mm.